

Internal/External Putty 634

Internal/external wall putty with especially smooth finish, in thickness up to 8 mm. **in one layer**. Suitable as a finish layer on precast concrete ceilings, concrete blocks, Ytong blocks and cement plaster. Available in white or gray.



Main Properties and Adjustment:

- Can be applied in thickness of approx. 8 mm.
- Adhesion strength of approx. 1 MPa
- Suitable for flattening walls and precast concrete ceilings, Ytong blocks and cement plaster.
- Serving as background for paint and colorful plaster spray.



Packaging:	25 Kg. paper bag, 5 kg. small bag
Consumption:	approx. 1.2 kg/m ² in 1 mm. thickness.
Composition:	white cement, aggregates and special polymeric admixtures
Substrate:	suitable for application on walls, precast concrete ceilings, Ytong blocks and cement plaster

Technical Data:

Wet bulk density	1.4 kg./liter
Bulk density after drying	1.1-1.2 kg./liter
Restraint shrinkage	Without cracks in the ring

Application:

- Rinse the wall with water, remove dust, dirt and oils.
- Cut off metal wires, remove nails and wooden parts, remove protruding and loose gravel.
- Pour into the mixing container approx. 9-10 liter of water. Slowly add the entire 25 Kg. contents of the bag, while mixing in a mixer to obtain a uniform mixture. Wait for 3 minutes and mix again.
- Water quantities could vary, despite that stated above, due to changes of weather and the like. In any event, the appropriate workability level ought to be achieved.
- Apply a first layer of in thickness of approx. 8 mm. and wait for an initial drying.
- If an additional layer is required, apply External Putty 634 in additional thickness of up to 8 mm.
- In order to flat the wall, it is possible to use a sponge trowel followed by metal trowel until obtaining a smooth and uniform finish.
- No need for curing.

Internal/External Putty 634

Note:

In order to obtain high adhesion strength, a thin layer of the material should be applied and compacted to the substrate, while applying the second layer up to the desirable thickness.

Precautions:

- External Putty 634 should not be applied on a wet wall. It is possible to apply on a moist wall.
- External Putty 634 should not be applied in surface temperatures under 5°C or above 35°C.
- Do not add water to a drying mix.

Cleaning: Tools and hands should be cleaned with running water, for as long as the material is fresh.

Storage: In its original package in a shaded and dry location.

Shelf Life: Up to 9 months from the production date.



The Technical Service Department is available to our customers for consultation and guidance. The materials marketed by us are made of the finest components and are under close quality control. However, liability for the adjustment of the material to its use is imposed on the user only. We recommend in any event testing the adjustment of the material to the sought application prior to its use.